

## DATA SHEET -DRAFT

Edition: 1.

Number: 0101C209D

Vallid from: 30.06.2020

Trade name: **JKI SUPER**  
**SC19026/031019/01**

Raw material: polyolephine

### Characteristics:

| Property   | Standart                             | Unit             | Min                          | Target | Max |     |
|--|--------------------------------------|------------------|------------------------------|--------|-----|-----|
| Lenght   | EN 1848-2                            | m                | 30                           |        |     |     |
| Width  | EN 1848-2                            | m                | dle objednávky (-0,5% / +1%) |        |     |     |
| Basis weight   | EN 1849-2                            | g/m <sup>2</sup> | 250                          | 270    | 290 |     |
| Tensile strenght                                     | MD                                   | EN 12311-1       | N/50 mm                      | 200    | 300 | 400 |
|  | CD                                   | EN 12311-1       | N/50 mm                      | 200    | 300 | 400 |
| Elongation   | MD                                   | EN 12311-1       | %                            | 40     | 60  | 80  |
|  | CD                                   | EN 12311-1       | %                            | 40     | 60  | 80  |
| Nail tear resistance                                 | MD                                   | EN 12310-1       | N                            | 80     | 150 | 250 |
|  | CD                                   | EN 12310-1       | N                            | 80     | 150 | 250 |
| Water collum   | EN 20811                             | cm               | > 300                        |        |     |     |
| Resistance to water penetration                      | EN 13984,<br>EN 1928, method A       | class            | W1                           |        |     |     |
| Breathability  | EN 13984,<br>EN 1931                 | m                | -                            | -      | -   |     |
| fire resistance                                      | ČSN EN 13501-1                       | class            | F                            |        |     |     |
| Durability of water vapour resistance against ageing | ČSN EN 13984,<br>EN 1296,<br>EN 1931 | m                | -                            | -      | -   |     |

All information and data were given according to the best of our knowledge. No warranty claims can be based on this data and information. We reserve the right to make technical modifications, in regards to product improvement or due to changes in our manufacturing process.

|                                  |            |                     |
|----------------------------------|------------|---------------------|
| Created:<br>Ing. Romana Luběnová | Signature: | Date:<br>30.06.2020 |
|----------------------------------|------------|---------------------|

|                                |            |                     |
|--------------------------------|------------|---------------------|
| Approved:<br>Ing. Jan Čeřovský | Signature: | Date:<br>30.06.2020 |
|--------------------------------|------------|---------------------|

|                        |            |       |
|------------------------|------------|-------|
| Confirmed by customer: | Signature: | Date: |
|------------------------|------------|-------|