

# TECHNICAL DATA SHEET



Product name:

## FIBRANskin SMART

Material:

HD-PE with polymeric coating

Application:

Plastic and rubber vapour control layers EN 13984

Vapour retarder membrane for

- Ventilated pitched roofs
- External walls with internal dry-lining

PROPERTY	METHOD	UNITS	NOMINAL VALUE	MINIMUM	MAXIMUM
Product designation according to EN 13984			B		
FUNCTIONALITY: WATER VAPOUR TRANSMISSION AND WATER TIGHTNESS					
Water vapour transmission range ( $\underline{S_d}$ )		m	0,2...35	-	-
Water vapour transmission ( $\underline{S_d}$ )	EN 1931	m	13	8	18
Density of water vapour flow rate (g)	EN 1931	kg / (m <sup>2</sup> .s)	3,16E-08	5,14E-08	2,28E-08
Temperature resistance	-	°C	-	-40	+80
Water tightness	EN 13859-1 based on EN 1928 (A)	class	W1	-	-
Durability (exposure to artificial ageing) Water vapour transmission properties	EN 1931	pass / no pass	(+)	-	-
Gurley airpermeability	ISO 5636/5	s	2.000	-	-
PHYSICAL AND MECHANICAL PROPERTIES					
Mass per unit area	EN 1849-2	g/m <sup>2</sup>	92	86	98
Thickness	EN 1849-2	mm	0,200	-	-
Reaction to fire (EN 13501-1)	EN ISO 11925-2	euroclass	E	-	-
Maximum tensile force (MD)	EN 12311-2	N/50mm	380	320	-
Elongation at max. tensile force (MD)	EN 12311-2	%	17	12	-
Maximum tensile force (XD)	EN 12311-2	N/50mm	380	330	-
Elongation at max. tensile force (XD)	EN 12311-2	%	20	14	-
Resistance to tearing MD (nail shank)	EN 12310-1	N	70	45	-
Resistance to tearing XD (nail shank)	EN 12310-1	N	65	40	-
ADDITIONAL PROPERTIES					
Length	EN 1848-2	mm	50.000	-	-
Length deviation	EN 1848-2	deviation in %	0	0	-
Width	EN 1848-2	mm	1.500	-	-
Width deviation	EN 1848-2	deviation in %	0	-0,5	+1,5
Straightness	EN 1848-2	mm/10m	-	-	75
Resistance to impact	EN 12691	mm	(+)	-	-
Joint strength	EN 12317-2	N/5cm	-	280	-
Water column	EN 20811	m	3	-	-
Durability (against alkali)					
MD elongation at max. tensile force	EN 12311-2	pass / no pass	pass	-	-
XD elongation at max. tensile force	EN 12311-2	pass / no pass	pass	-	-

(+): No Performance Determined



Issuing date: 14/11/2018

First CE marking: 12/10/2017

Copyright © 2018 FIBRAN S.A. 56010, Thessaloniki, Greece. All rights reserved. FIBRANskin is a registered trademarks or trademarks

Some test methods are modified according to the EN 13859-2:2014 and/or according to the FIBRAN ISO 9001:2008 certified quality system (for details please contact your regional FIBRAN representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, FIBRAN makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature