

FONOSCUDO



ΤΕΧΝΙΚΑ ΧΑΡΑΚΤΗΡΙΣΤΙΚΑ	U.M.	FONOSCUDO
Μη πλεχτό Πολυστερικό Ύφασμα	mm	~ 6,5
Ήχου Ελαστικό Στρώμα	mm	~ 1,5
Συνολικό Πάχος	mm	~ 8
Μήκος	m	10
Πλάτος	m	1
Πλάτος μη Υφαντής Πολυεστερικής Επιφάνειας	cm	100
Επικάλυψη	cm	5
Μήκος Ηχομονωτικού Υλικού FONOSCUDO	cm	105
Διαπερατότητα		waterproof
Ατμοδιαπερατότητα	ad.	$\mu > 100.000$
Συντελεστής Θερμικής Αγωγιμότητας	W/mK	$\lambda = 0,17$
Συντελεστής Θερμικής Αγωγιμότητας μή Υφαντού Πολυεστέρα	W/mK	$\lambda = 0,045$
ΑΚΟΥΣΤΙΚΗ ΗΧΟΜΟΝΩΣΗ στο ΔΑΠΕΔΟ		
Επίπεδο εκπομπής Θορύβου ISO στα 500 Hz, γυμνό Δάπεδο	L_{nwo}	73,5 dB
Επίπεδο εκπομπής Θορύβου ISO στα 500 Hz, με FONOSCUDO	L_{nw}	45,5 dB
Βελτίωση ως αποτέλεσμα της Διαφοράς μεταξύ επιπέδων	$\Delta L = L_{nwo} - L_{nw}$	28 dB

TECHNONICOL ITALIA srl reserves the right to modify the technical data in this specification sheet which is based on current production without prior warning.

All indications in this specification sheet are based upon our experience and current working practices.

www.technicol.it

ΔΙΑΘΕΣΗ ΚΑΙ ΔΙΑΝΟΜΗ ΑΠΟ ΤΗΝ Ν.ΠΑΠΑΙΑΝΝΙΔΗΣ ΥΙΟΣ ΟΕ / www.monotex.gr www.technicol.it, info@technicol.it

TECHNONICOL ITALIA s.r.l.

Via Galoppat, 134 – 33087

Pasiano di Pordenone (PN), Italia

P.IVA 01745250934 - REA PN - 101202

Tel.: 0434-614611, Fax: 0434-628178