

**NINGBO LEADWIN INTERNATIONAL TRADE CO.,LTD**  
**Ceramic Fiber Paper Data Sheet**

Item	Standard	Test Value	Result	Test Basis
Al <sub>2</sub> O <sub>3</sub> (%)	52-55	53.6	PASSED	GT/T16400-2015
SiO <sub>2</sub> (%)+Al <sub>2</sub> O <sub>3</sub> (%)	≥98	98.22	PASSED	
Fe <sub>2</sub> O <sub>3</sub> (%)	≤0.20	0.18	PASSED	
Burning reduction(%)	≤10	9	PASSED	
Volum densityKg/m <sup>3</sup>	200±15	210	PASSED	
Slag ball content agreement(%)	≤20.0	8	PASSED	
Tensile strength Kpa	≥200	232	PASSED	