

# EcoRoof rectangular

ETA 10-0452

General description: coloured asphalt shingle



bituminous compound	-		<b>Blown bitumen</b>	
length	EN 544	mm	<b>1000</b>	<b>+/-3</b>
width	EN 544	mm	<b>340</b>	<b>+/-3</b>
thickness	-	mm	<b>3</b>	<b>+/-10%</b>
exposed area	-	mm	<b>145</b>	-

## Physical-chemical properties

weight	-	kg/m <sup>2</sup>	<b>9,4</b>	<b>+/-8%</b>
mass of the fibreglass mat	-	g/m <sup>2</sup>	<b>100</b>	<b>+/-10%</b>
bitumen	EN 544	g/m <sup>2</sup>	<b>&gt;1000</b>	-
granules single layer	EN 544	g/m <sup>2</sup>	<b>&gt;1120</b>	-
mechanical resistance MD/CMD	EN 544	N/ 5 cm	<b>&gt;600/400</b>	-
nail resistance	EN 544	N	<b>&gt;100</b>	-
granules adhesion	EN 544	-g	<b>&lt;1,2</b>	-

## Fire behaviour

classification according	EN 13501-5	<b>B roof (t1)</b>
classification according	EN 13501-1	<b>E</b>

## Wrapping

type	<b>polyethylene</b>
shingles for bundle	<b>16</b>
m <sup>2</sup> /bundle	<b>2,32</b>
m <sup>2</sup> /pallet	<b>185,6</b>

Further info about company, product and roofing instruction on web site [www.tegola canadese.com](http://www.tegola canadese.com)

Tegola Canadese S.p.A.  
Via dell'Industria, 21- 31029 Vittorio V.to (TV) - I -  
Tel. +39.0438.91111 - Fax +39.0438.911260  
e-mail: [info@tegolacanadese.com](mailto:info@tegolacanadese.com)

**TEGOLA**<sup>®</sup>   
CANADESE

Company certified according quality system ISO 9001 and environmental system ISO14001